



1. Users manual

	FINESTO FLEXSTONE Rawmaterial jointless application			
Technical data of primary material	Approximately 2,80 mtr x 1,20 mtr (untrimmed)			
Transport und stocking	<p>Transport of Flexstone sheets delivered flat on pallets. Transport of Flexstone can also be delivered up to a maximum of 3 sheets rolled on a tube. It is important to store Flexstone sheets always in a flat position on pallets, with temperatures not less than 5°C. Before installing Flexstone sheets, material and working conditions shall be at min. 5°C.</p>			
Surface conditions	<p>Before gluing examine and access the surface where material is to be applied. Surface must be primed before installing Flexstone sheets.</p>			
Adhesive requirements	Surface	Inside (dry)	Inside (wet)	Outside (facade)
	Cement- / Lime cement plaster	Dispersion glue (Contact glue procedure)	Natural stone glues	Natural stone glue
	Gypsum plaster	Dispersion glue	Natural stone glues	Natural stone glue
		(Contact glue procedure)		
	Concrete	Dispersion glue	Natural stone glues	Natural stone glue
		(Contact glue procedure)		
	Rigid foam board	Dispersion glue	Natural stone glues	Natural stone glue
		(Contact glue procedure)		
	Plasterboard	Dispersion glue	Natural stone glues	Natural stone glue
		(Contact glue procedure)		
	Metal	PUR glues*	PUR glues*	PUR glues*
	Plastics	Neoprene- Contact glues		Neoprene- Contact glues

* Polyurethan reaction glue

It is important to follow adhesive manufacturer instructions

<p>Processing</p>	<p>FINESTO FLEXSTONE is a natural product and characterized by a large variance in optics, structures, colours and isopatch lines.</p> <p>To attain the designated general view (monolith) of the wall area a presort of rawmaterial is recommended.</p> <p>The backside of the raw material sheet has to be clean and dustfree.</p> 
<p>Installation</p>	<p>Usage of solvent or solvent free adhesive for rawmaterial jointless applications:</p> <p>adhesive must be applied to both the surface that the material is to be applied to and also the underside of the Flexstone sheet to achieve maximum contact. (contact glue procedure)</p> <p>Always follow the Instructions of adhesive manufacturer.</p> <p>To achieve jointless installation firstly select the Flexstone sheets required.</p> <p>Install first sheet as recommended followed by the second sheet allowing for a overlap of 5-10cm on vertical cuts and 10-25cm on horizontal cuts.</p> <p>Cut through both sheets using a suitable cutting knife, apply more adhesive to underside of material at edges if required, warm up joint area using a suitable fan heater gun and carefully bring both edges together using a timber shaped wedge if required.</p> <p>Excess adhesive that may have got onto the surface of the material must only be removed after adhesive has completely dried.</p>

Applying of Standard primer	<p>After adhesive has fully dried primer must always be applied to complete finished surface.</p> <p>For vertical installations you must always apply primer starting at the base working upwards.</p> <p>It is important that the surface is completely primed.</p> <p>While material is still moist after applying primer, it is possible to repair any small defects that may have occurred on the surface of the material.</p>
Applying of Sealer	<p>As an additional surface protection against wet and dust you must always apply FINESTO sealer with a suitable paint roller, the sealer waterproofs and protects the surface from dirt etc. additional coats of sealer will be required in areas such as bathrooms, wellness etc. always apply undiluted, it is most important that the surface is completely sealed.</p>
Applying Façade sealer	<p>Facade sealer must always be applied for external installations such as facades, walls etc.</p> <p>The surface and Flexstone sheets shall not be installed at temperatures below 5°C.</p> <p>Note: facade sealer shall require three applications of sealer to waterproof facade and also protect from graffiti.</p>
Additional information	<p>Any larger defects to Flexstone sheets that maybe caused by transport etc. can easily be repaired by installing an inlay of Flexstone sheet material After installation carefully clean the surface with a broom. Don't sweep material out of the closed joints.</p> <p>To close connection- and expansion joints between FINESTO FLEXSTONE and concrete, plaster, glass, wood, metal, ceramics or PVC use special natural stone – silicon.</p> <p>Natural stone silicon may also be applied where expansion may occur between Flexstone sheet material and surfaces.</p>

FINESTO

Flexible Stone | Wallpaper





FINESTO Dekorasyon Sanayi ve Ticaret LTD ŞTİ

Flexiable Stones I Wallpaper I Accessories

Merkez Mahallesi Kuşçu Sokak No:5/A

İstanbul /Türkiye

www.finestogroup.com
info@finestogroup.com